

Adhesion Promoter V2

Colourless Adhesion Promoter on silane basis for SMP and silicone sealants. Adhesion Promoter V2 is universally usable for non-absorbent substrates.

Materials

e.g. glass, ceramics, metals as well as various plastics.

Technical data

| | |
|---------------------------|---|
| Appearance | liquid, transparent |
| Packaging | 250 ml, 1 L, 10 L |
| Odour | characteristically as solvent |
| Shelf life | 12 months from production date in the unopened original packaging |
| Storage | dry and cool |
| Drying time at 20°C | at least 10 minutes, max. 2 hours |
| Lower working temperature | +5°C |
| Viscosity | low-viscous |
| Density | 0.808 ± 0.02 g/cm ³ |

All measurements were performed under normal conditions (23 °C and 50 % relative humidity).

Application

Adhesion Promoter V2 can be put on with a paintbrush in a thinner shift on the cleaned, fat-free and dry surface; or used as a wash-Adhesion Promoter (put on the Adhesion Promoter onto a tissue and then clean the surface) as primary treatment of the surface. The open-time is at +20°C at least 10 minutes. At the latest 2 hours after putting on the Adhesion Promoter the application of the sealant or adhesive is to be done (at long waiting times the surface must be controlled again for cleanness). May leave stains which are difficult to remove from the substrate. Do not wait until residues are dried up, remove immediately.

General information

Adhesion Promoter must be applied in thin shift, according to the surface, onto the cleaned, fat-free and dry surfaces. Antecedent the application of the sealant the solvent must have evaporated. The indicated drying times are to be kept. Most Adhesion Promoters contain inflammable solvents and are moisture-sensitive. Therefore it is recommended to close the containers immediately after application. Adhesion Promoters leave on all surfaces more or less visible remains. Adhesion Promoter spilled or unintentionally applied must be wiped off immediately. After drying the Adhesion Promoter can only hardly be removed. For this reason, covering the surfaces around the joints with tape is urgently recommended. Keep the Adhesion Promoters are flammable. Storage in original packaging in well air-conditioned and dry rooms. Take further safety information from the security data sheet and the print on the packaging. We make attentive that these Adhesion Promoters where necessary, are a component of the adhesive system.

Technical data sheet Adhesion Promoter V2

Work and environmental safety

Important information about work and environmental safety is available on the material safety data sheet.

merz+benteli ag

Freiburgstrasse 616
CH - 3172 Niederwangen
Phone +41 31 980 48 48
Fax +41 31 980 48 49
info@merz-benteli.ch
www.merz-benteli.ch

Last Update: 10.06.2020

Our information is based on experiences in lab and practice. Their publication occurs, however, without takeover of a liability for damages and losses which are to be put down to these information, as there the practical application conditions are lying outside of the enterprise's control. The user is not released from the necessity to carry out own attempts for the planned applications under practical conditions. Due to the different materials, processing methods and local factors onto which we have no influence, no guarantee – also in patent-legal respect – can be taken over. We recommend therefore sufficient own attempts. By the way we refer to our General Business Conditions. Technical characteristics according to the Technical Data Sheets up to their expiry date which is available upon request and which is available on our website. Technical changes reserved. Contents examined and released by merz+benteli ag, CH - Niederwangen/Berne